



RENITHERM[®] PMW TC

Solvent based transparent top coat for Renitherm[®] PMW

Uses:	Top coat for wood which is treated with Renitherm [®] PMW transparent base coat. Protects from wear and humidity.
Colour	Transparent
Gloss grade	Matt, satin gloss
Application	Brushing, rolling, spraying
Consumption	50 - 100 g / m ²
Preparation of substrate	Apply Renitherm [®] PMW-TC on completely dried coats of Renitherm [®] PMW only; i.e. after 2 days drying time, depending on temperature and humidity.
Application hints	Stir well before use. Don't apply below +10°C and >80% rel. humidity. Apply undiluted in supply viscosity. Tip size: Airless 0.013" / Air 1.2 mm
Cleaning of equipment	Universal solvent
Drying time	At +20°C, 60 % R.H. <ul style="list-style-type: none">- dust dry after 120 minutes- complete dry after 24 hrs
Flash point	+ 61°C
Density	Approx. 0,83 g / cm ³ at 20 °C
Packing	5 kg and 10 kg cans
Transport classification	VbF: A III; RID/ADR: n/a
Storage	12 months in original closed containers.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be constructed as guaranteeing specified properties of products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.

The logo for RENITHERM, featuring a stylized red flame icon above the word "RENITHERM" in a bold, black, sans-serif font. A registered trademark symbol (®) is located to the upper right of the word.

AUDAX-Keck GmbH, Weiherstr. 10, 75365 Calw / Germany



+49 7051 1625-0



+49 7051 1625-50



fire@audax.de

www.audax.de